PRINT-MAT 900

Product-description

Sap code	**14011453**
Pile material	**100% PES**
Bonding	**The product is mechanically bonded by needling.**
Colour	**Ecru**
Backing	**GELFOAM**

Analysis

PARAMETER		METHOD	VALUE	SPECIFICATIONS		
pile weight		ISO 9073-1	**300 g/m²**	270	- 330	g/m²
pile thickness (1) -	@2kPa	ISO 9073-2	**2,00 mm**	1,80	- 2,20	mm
total weight (2)		ISO 9073-1	**900 g/m²**	810	- 990	g/m²
total thickness (1)(2) -	@2kPa	ISO 9073-2	**2,80 mm**	2,50	- 3,10	mm

(1) measured before packaging & transport (2) no printed

Customer information

Standard width (cm) **160 - 200 - 320 - 400**

Toleration on Width ***min 0 - max +2cm***

Standard length (*) **25 lm**

Toleration on length ***min 14 - max 30lm***

Inner diameter tube (*) **76mm/3 inch**

Packaging **The roles are properly wrapped up in PE-foil.**
The tube may stick out maximum 1cm at both sides.
Completely straight roles within ±5cm.

(*) Special length/packaging : on demand.

Usage **Fire resist - EN 13501-1 : Cfl-S1**
Sound absorption : α_w = 0,10 (H)
Impact sound insulation : ΔL_w = 18dB
Technical class DS -EN 13893 : μ = 0,32

MATEN®
www.mat-en.com

Aderente ad AIB

Made in Italy

CSI CERT ISO 9001
Sistema di gestione qualità accreditato